

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 08-245880

(43)Date of publication of application : 24.09.1996

(51)Int.Cl. C08L 83/00

// C08G 77/62

(21)Application number : 07-079644 (71)Applicant : TONEN CORP

(22)Date of filing : 10.03.1995 (72)Inventor : TASHIRO YUJI
SUZUKI SUNAO

(54) HEAT-RESISTANT FILM AND ITS PRODUCTION

(57)Abstract:

PURPOSE: To obtain a highly heat-resistant film by forming a silicon copolymer comprising structural units represented by specific formulas into a film.

CONSTITUTION: A silicon copolymer having structural units represented by formulas I to V (wherein R1 and R2 are each alkyl, cycloalkyl, etc.; R3 is alkylene, alkenylene, etc.; II, m, and n are each 1 or higher; and o and p are each 0 or a positive integer) is obtd. by dissolving a diamine (e.g. p-phenylenediamine) in a solvent (e.g. xylene) in an N2 atmosphere, dissolving a disilyl compd. [e.g. an organohydrodihalosilane, an organodihalosilane, or 1, 4-bis(dimethylchlorosilyl)benzene] in the soln. under heating, adding an amine to the resulting soln. to capture hydrochloric acid generated by the reaction, cooling the soln. to about 30°C or lower, adding NH3 to react it with unreacted halogenosilane, removing unreacted NH3 after the reaction, filtering the soln. under pressure, and removing the solvent. The copolymer is formed into a film and cured at 200-500°C in an N2 atmosphere to give a low-birefringence film having a refractive index of 1.45 or higher.

LEGAL STATUS [Date of request for examination] 28.02.2002

[Date of sending the examiner's decision of rejection] 02.04.2004


[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]





[Date of registration]

[Number of appeal against examiner's decision of rejection]



[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]



Copyright (C); 1998,2003 Japan Patent Office